

H-ZBaF50	658509
-----------------	---------------

nd =1.65844	vd =50.85	nF - nC =0.012948
ne =1.66152	ve =50.57	nF' - nc' =0.013082

Refractive Indices		
	λ (nm)	
n_r	706.5	1.65235
n_c	656.3	1.65454
$n_{c'}$	643.8	1.65516
n_{He-Ne}	632.8	1.65574
n_D	589.3	1.65832
n_d	587.6	1.65844
n_e	546.1	1.66152
n_F	486.1	1.66749
$n_{F'}$	480.0	1.66824
n_g	435.8	1.67471
n_h	404.7	1.6808
n_i	365.0	1.69138

Constants of Dispersion (Cauchy)	
A_0	2.6934245
A_1	$-8.63701401 \times 10^{-3}$
A_2	$2.04964501 \times 10^{-2}$
A_3	$-9.32054531 \times 10^{-5}$
A_4	$6.27097471 \times 10^{-5}$
A_5	$-2.08346521 \times 10^{-6}$

Relative Partial Dispersions			
$P_{d,c}$	0.2919	$P'_{d,c'}$	0.2416
$P_{e,d}$	0.2471	$P'_{e,d}$	0.2446
$P_{g,F}$	0.5575	$P'_{g,F'}$	0.4946

Deviation of Relative Partial Dispersions	
$\Delta P_{F,e}$	-0.0011
$\Delta P_{g,F}$	-0.0016

NHG	HOYA	OHARA	SCHOTT
H-ZBaF50	BaCED5	S-BSM25	N-SSK5

Chemical Properties	
	Group
RC(S)	1
RA(S)	3
DW	1
DA	3

Thermal Properties	
T_g (°C)	639
T_S (°C)	687
$T_{10}^{14.5}$ (°C)	589
T_{10}^{13} (°C)	626
$\alpha_{20/120^\circ C}$ ($10^{-7}/K$)	75.01
$\alpha_{20/300^\circ C}$ ($10^{-7}/K$)	85.76

Mechanical Properties	
Hardness ($10^7 Pa$)	508
FA (Relative Abrasion)	
Young's Modulus ($10^7 Pa$)	8592
Rigidity Modulus ($10^7 Pa$)	3359
Poisson's Ratio	0.279

Photoelastic Constant	
β ($10^{-12}/Pa$)	2.34

Color	
λ_{80}/λ_5	38/34

Specific Gravity	
ρ (g/cm^3)	3.90

Internal Transmittance		
λ (nm)	τ_{5mm}	τ_{10mm}
2400	0.906	0.82
2200	0.956	0.914
2000	0.982	0.965
1800	0.991	0.982
1600	0.996	0.993
1400	0.997	0.995
1200	0.999	0.998
1060	0.999	0.998
1000	0.999	0.998
950	0.999	0.998
900	0.999	0.998
850	0.999	0.996
800	0.997	0.994
700	0.996	0.992
650	0.995	0.991
600	0.995	0.991
550	0.995	0.991
500	0.994	0.988
480	0.992	0.985
460	0.991	0.982
440	0.989	0.979
420	0.987	0.974
400	0.977	0.954
390	0.963	0.928
380	0.938	0.88
370	0.88	0.78
360	0.76	0.58
350	0.54	0.29
340	0.21	0.05
330		
320		
310		
300		
290		
280		



Naked Optics Corp.
 16 Mt. Bethel Rd. #374
 Warren, NJ 07059
 908-685-0352 (ph) . 908-325-0250 (fax)

Naked Optics Corp.
16 Mt. Bethel Rd. #374
Warren, NJ 07059
908-685-0352 (ph) . 908-325-0250 (fax)